

## 2K PU Hardener

FOR PROFESSIONAL USE ONLY

### Description

2K PU hardener is an isocyanate based curing agent, to be applied in combination with 2K PU S series solid colors, 2K PU primers and 2K PU clear coats.

### Product name

2K PU hardener A801 / A802 / A803


### Hardener

A803 Slow drying Hardener, to be used at 25-35 °C

A802 Standard Hardener, to be used at 15 °C-25 °C

A801 Fast drying Hardener, to be used at 5-15 °C

### Mixing



S Series: Hardener = 2:1

A850: Hardener = 2:1

A851: Hardener = 2:1

A852 : Hardener = 2:1

A8833: Hardener = 3:1

A853: Hardener = 2:1

A855: Hardener = 2:1

A856: Hardener = 2:1

A831: Hardener = 4:1

Mix thoroughly!

### Pot-life

Slow dry Hardener 4 hours at 20 °C

Standard Hardener 4 hours at 20 °C

Fast dry Hardener 4 hours at 20 °C

### Cleaning of equipment

Onwings solvents

### Product storage

1. The hardeners are flammable, store under safe conditions in a cool and dry place.
2. Avoid human skin contact and inhalation of vapours.
3. Close the tin immediately after use.

### Product stability

Product shelf-life is 2 years when products are stored unopened at 20 °C. Avoid extreme temperature fluctuation.